

WHITE



# FJORD

Wood Look

4x24


# TILE

AMERICA

SHADE VARIATION

V3 - Moderate Variation

While the colors present on a single piece of tile will be indicative of the colors to be expected on the other tiles, the amount of colors on each piece may vary significantly. For example “that little bit of color” on one piece of tile may be the primary color on the next piece.



COFFEE



BROWN



GRAY



BLUE



DARK



WEAR CODE

White, Blue & Grey: Class 4 All Residential and Light Commercial Applications. Class 4 tiles may be used in all residential areas and light commercial applications.

Brown, Coffee & Dark: Class 3 Residential Applications. Suitable for all residential applications.

PERFORMANCE DATA

THICKNESS: 9.6 mm

Characteristics:	Norms:	Results
Water Absorption	ISO 10545-3	≤ 0.5%
Abrasion Resistance	ISO 10545-7	3 / 4
Breaking Strength	ISO 10545-4	35-45 N/mm <sup>3</sup>
Dynamic Coefficient of Friction	AcuTest	> 0.42
Dimensions Range	ISO 10545-2	Conforms
Frost Resistance	ISO 10545-12	Frost Proof
Chemical Resistance - Household Chemicals	ISO 10545-13	A
Chemical Resistance - Low Concentration of Acids	ISO 10545-13	Conforms
Resistance to Stains	ISO 10545-14	Class 5
Crazing Resistance of Glazed Tiles	ISO 10545-11	Resists

### Notes:

Per ANSI standard A108.02,4.3.82, joints on tiles longer than 15” should not be staggered more than 1/3 the length of the tile.  
Dynamic Coefficient of Friction (DCOF) is > 0.42 Wet.  
The Minimum Recommended Grout Joint for Non-Rectified tiles is no less than 3/16”.

Book An Appointment



www.tileamerica.com